



# ALFA FASADA

## White EPS boards



$\lambda$   
**0,040**  
**W/mK**



walls and facade  
thermal insulation



easy assembly



economic  
solutions

### DESCRIPTION

ALFA FASADA polystyrene boards comply with the following standard code: EN 13163:2012  
**EPS-EN 13163-T1-L2-W2-Sb2-P5-BS80-TR80**

These boards are produced with a polystyrene foaming method.

**Accessible sizes:** 1000 x 500 [mm]

**Board thickness:** from 10 [mm], in increments of 10 [mm]

**Edges' trim:** smooth or milled overlapping edges (trim size – 15 [mm])

### ATTENTION

- The polystyrene boards should not come into direct contact with substances harmful to polystyrene, e.g. organic solvents such as acetone, benzene, turpentine or gasoline.
- The polystyrene boards should be stored protected from damages and exterior conditions.

#### SALES TO DISTRIBUTORS

Contact for distributors of building materials.  
Information about where to buy products.

[yetico.com/contact](http://yetico.com/contact)


#### SALES TO INVESTORS

Contact for investors (business and individual),  
contractors, architects, and designers.

[yetico.com/contact](http://yetico.com/contact)

## BASIC USES

- external thermal insulation performed with a light-wet method [ETICS]
- external thermal insulation performed with a light-dry method
- external insulation in interior partition walls.
- external horizontal thermal insulation of:
  - roofs with cladding from the inside
  - floors between joists
  - light framed roofs with cladding
  - spaces between rafters
  - ventilated roofs



## DOCUMENTS

- Declaration of performance no. 04-DoP-2018 with the standard code EN 13163:2012.
- Hygienic approval EPS no. HK/B/0921/02/2018

## THERMAL RESISTANCE – dependent on product thickness

Thickness [mm]																			
10	20	30	40	50	60	70	80	90	100	110	120	130	140	150	160	170	180	190	200
Thermal resistance RD [m <sup>2</sup> K/W]																			
0,25	0,50	0,75	1,00	1,25	1,50	1,75	2,00	2,25	2,50	2,75	3,00	3,25	3,50	3,75	4,00	4,25	4,50	4,75	5,00



## PACKAGING METHOD

Specification	Volume of packages, size of boards and number of items per package depend on board thickness																			
Thickness [mm]	10	20	30	40	50	60	70	80	90	100	110	120	130	140	150	160	170	180	190	200
Items per package	60	30	20	15	12	10	8	7	6	6	5	5	4	4	4	3	3	3	3	3
Package volume (smooth edges) [m <sup>3</sup> ]	0,300	0,300	0,300	0,300	0,300	0,300	0,280	0,280	0,270	0,300	0,275	0,300	0,260	0,280	0,300	0,240	0,255	0,270	0,285	0,300
Package volume (milled edges) [m <sup>3</sup> ]	x	x	x	x	x	x	x	0,268	0,258	0,287	0,263	0,287	0,248	0,268	0,287	0,229	0,244	0,258	0,272	0,287
Covering area of package (smooth edges) [m <sup>2</sup> ]	30,0	15,0	10,0	7,50	6,00	5,00	4,00	3,50	3,00	3,00	2,50	2,50	2,00	2,00	2,00	1,50	1,50	1,50	1,50	1,50
Covering area of package (milled edges) [m <sup>2</sup> ]	x	x	x	x	x	x	x	3,34	2,87	2,87	2,39	2,39	1,91	1,91	1,91	1,43	1,43	1,43	1,43	1,43

## PARAMETERS

Board type		Alfa Fasada	
Product code (declared level or class properties of products)		EPS-EN 13163-T1-L2-W2-S <sub>b</sub> 2-P5-BS80-TR80	
Declared product properties conform to EN 13163:2012 standard	Measuring unit	Requirements or tolerances	
		Class or level codes	Values
Thickness (dimensional tolerance class)	[mm]	T1	1
Length (dimensional tolerance class)	[mm]	L2	2
Width (dimensional tolerance class)	[mm]	W2	2
Rectangularity over the length and width (dimensional tolerance class)	[mm/mm]	S <sub>b</sub> 2	2/1000
Flatness (dimensional tolerance class)	[mm]	P5	5
Flexural strength levels	[kPa]	BS80	80
Tensile strength perpendicular to faces	[kPa]	TR80	80
Declared thermal conductivity rate	[W/(m·K)]	[-]	0,040
Reaction to fire	From A to F	Euroclass	E





# ALFA FASADA

## HEADQUARTERS

YETICO S.A.  
ul. Towarowa 17a  
10-416 Olsztyn

+48 89 538 78 11  
yetico@yetico.com  
www.yetico.com

## CUSTOMER SERVICE

OLSZTYN  
+48 89 538 78 51 / 52

GALEWICE  
+48 62 783 80 89 / 25

GORZÓW WLKP.  
+48 95 720 97 01 / 02

TARNOBRZEG  
+48 539 609 072  
+48 532 916 779