

# BETA PASSIVE FASADA

## EPS boards with graphite



λ 0,032 W/mK



facade and walls thermal insulation



up to 30% better thermal insulation



low-energy construction

## **DESCRIPTION**

BETA PASSIVE FASADA polystyrene boards comply with the following standard code: EN 13163:2012. **EPS-EN 13163-T1-L2-W2-Sb2-P5-BS60.** 

These boards are produced with a polystyrene foaming method, based on materials with graphite to improve their thermal insulation properties.

Accessible sizes: 1000 x 500 [mm]

Board thickness: from 10 [mm], in increments of 10 [mm]

Edges' trim: smooth or milled overlapping edges (trim size – 15 [mm]

## ATTENTION

- The polystyrene boards should not come into direct contact with substances harmful to polystyrene, e.g. organic solvents such as acetone, benzene, turpentine or gasoline.
- The polystyrene boards should be stored protected from damages and exterior conditions.
- Due to higher absorption of UV radiation graphic boards should be protected from direct exposure to the sun during transportation, as well as in storage within construction sites.

## **SALES TO DISTRIBUTORS**

Contact for distributors of building materials. Information about where to buy products.

yetico.com/contact

## SALES TO INVESTORS

Contact for investors (business and individual), contractors, architects, and designers.

yetico.com/contact

## **BASIC USES**

- external thermal insulation performed with a light-wet method [ETICS]
- external thermal insulation performed with a light-dry method
- external insulation in interior partition walls
- external horizontal thermal insulation of:
  - roofs with cladding from the inside
  - floors between joists
  - light framed roofs with cladding
  - spaces between rafters
  - ventilated roofs



## **DOCUMENTS**

- Declaration of performance no. 16-DoP-2018 with the standard code EN 13163:2012.
- Hygienic approval EPS-P no. HK/B/0921/02/2015.

## THERMAL RESISTANCE - dependent on product thickness

	Thickness [mm]																		
10	20	30	40	50	60	70	80	90	100	110	120	130	140	150	160	170	180	190	200
	Thermal resistance RD [m²K/W]																		
0,30	0,60	0,90	1,25	1,55	1,85	2,15	2,50	2,80	3,10	3,40	3,75	4,05	4,35	4,65	5,00	5,30	5,60	5,90	6,25



## PACKAGING METHOD

Specification				Volum	e of pa	ckages	, size o	f board	s and n	umber	of item	s per p	ackage	depen	d on bo	ard thi	ckness			
Thickness [mm]	10	20	30	40	50	60	70	80	90	100	110	120	130	140	150	160	170	180	190	200
Items per package	60	30	20	15	12	10	8	7	6	6	5	5	4	4	4	3	3	3	3	3
Package volume (smooth edges) [m³]	0,300	0,300	0,300	0,300	0,300	0,300	0,280	0,280	0,270	0,300	0,275	0,300	0,260	0,280	0,300	0,240	0,255	0,270	0,285	0,300
Package volume (milled edges) [m³]	х	х	х	х	х	х	х	0,268	0,258	0,287	0,263	0,287	0,248	0,268	0,287	0,229	0,244	0,258	0,272	0,28
Covering area of package (smooth edges) [m²]	30,0	15,0	10,0	7,50	6,00	5,00	4,00	3,50	3,00	3,00	2,50	2,50	2,00	2,00	2,00	1,50	1,50	1,50	1,50	1,50
Covering area of package (milled edges) [m²]	х	x	x	x	x	x	х	3,34	2,87	2,87	2,39	2,39	1,91	1,91	1,91	1,43	1,43	1,43	1,43	1,43

## **PARAMETERS**

Board type		Beta Passive Fasada							
Product code (declared level or class properties	of products)	EPS-EN 13163-T1-L2-W2-S <sub>b</sub> 2-P5-BS60							
Declared product properties conform to EN	Measuring	Requirements	or tolerances						
13163:2012 standard	unit	Class or level codes	Values						
Thickness (dimensional tolerance class)	[mm]	T1	1						
Length (dimensional tolerance class)	[mm]	L2	2						
Width (dimensional tolerance class)	[mm]	W2	2						
Rectangularity over the length and width (dimensional tolerance class)	[mm/mm]	S <sub>b</sub> 2	2/1000						
Flatness (dimensional tolerance class)	[mm]	P5	5						
Flexural strength levels	[kPa]	BS60	60						
Declared thermal conductivity rate	[W/(m·K)]	[-]	0,032						
Reaction to fire	from A to F	Euroclass	Е						





# SSIVE FASADA

## **HEADQUARTERS**

YETICO S.A. ul. Towarowa 17a 10-416 Olsztyn

+48 89 538 78 11 yetico@yetico.com www.yetico.com

## **CUSTOMER SERVICE**

OLSZTYN +48 89 538 78 51 / 52

GALEWICE +48 62 783 80 89 / 25

GORZÓW WLKP. +48 95 720 97 01 / 02

TARNOBRZEG +48 539 609 072 +48 532 916 779