



# GAMMA PASSIVE FASADA

EPS boards  
with graphite



$\lambda$   
**0,033**  
**W/mK**



facade and walls  
thermal insulation



up to 30% better  
thermal insulation



low-energy  
construction

## DESCRIPTION

GAMMA PASSIVE FASADA polystyrene boards comply with the following standard code: EN 13163:2012 **EPS-EN 13163-T1-L2-W2-Sb2-P5-BS60.**

These boards are produced with a polystyrene foaming method, based on materials with graphite to improve their thermal insulation properties.

**Accessible sizes:** 1000 x 500 [mm]

**Board thickness:** from 10 [mm], in increments of 10 [mm]

**Edges' trim:** smooth or milled overlapping edges (trim size – 15 [mm])

## ATTENTION

- The polystyrene boards should not come into direct contact with substances harmful to polystyrene, e.g. organic solvents such as acetone, benzene, turpentine or gasoline.
- The polystyrene boards should be stored protected from damages and exterior conditions.
- Due to higher absorption of UV radiation graphic boards should be protected from direct exposure to the sun during transportation, as well as in storage within construction sites.

### SALES TO DISTRIBUTORS

Contact for distributors of building materials.  
Information about where to buy products.

[yetico.com/contact](http://yetico.com/contact)

### SALES TO INVESTORS

Contact for investors (business and individual),  
contractors, architects, and designers.

[yetico.com/contact](http://yetico.com/contact)

## BASIC USES

- external thermal insulation performed with a light-wet method [ETICS]
- external thermal insulation performed with a light-dry method
- external insulation in interior partition walls
- external horizontal thermal insulation of:
  - roofs with cladding from the inside
  - floors between joists
  - light framed roofs with cladding
  - spaces between rafters
  - ventilated roofs



## DOCUMENTS

- Declaration of performance no. 03-DoP-2018 with the standard code EN 13163:2012.
- Hygienic approval EPS-P no. HK/B/0921/02/2015.

## THERMAL RESISTANCE – dependent on product thickness

| Thickness [mm]                             |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |
|--|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|
| 10   | 20   | 30   | 40   | 50   | 60   | 70   | 80   | 90   | 100  | 110  | 120  | 130  | 140  | 150  | 160  | 170  | 180  | 190  | 200  |
| Thermal resistance RD [m <sup>2</sup> K/W] |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |      |
| 0,30                                       | 0,60 | 0,90 | 1,20 | 1,50 | 1,80 | 2,10 | 2,40 | 2,70 | 3,00 | 3,30 | 3,60 | 3,90 | 4,20 | 4,50 | 4,80 | 5,15 | 5,45 | 5,75 | 6,05 |



## PACKAGING METHOD

| Specification   | Volume of packages, size of boards and number of items per package depend on board thickness |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |       |
|---|--|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|
|   | 10   | 20    | 30    | 40    | 50    | 60    | 70    | 80    | 90    | 100   | 110   | 120   | 130   | 140   | 150   | 160   | 170   | 180   | 190   | 200   |
| Thickness [mm]  | 10   | 20    | 30    | 40    | 50    | 60    | 70    | 80    | 90    | 100   | 110   | 120   | 130   | 140   | 150   | 160   | 170   | 180   | 190   | 200   |
| Items per package   | 60   | 30    | 20    | 15    | 12    | 10    | 8     | 7     | 6     | 6     | 5     | 5     | 4     | 4     | 4     | 3     | 3     | 3     | 3     | 3     |
| Package volume (smooth edges) [m <sup>3</sup> ]           | 0,300  | 0,300 | 0,300 | 0,300 | 0,300 | 0,300 | 0,280 | 0,280 | 0,270 | 0,300 | 0,275 | 0,300 | 0,260 | 0,280 | 0,300 | 0,240 | 0,255 | 0,270 | 0,285 | 0,300 |
| Package volume (milled edges) [m <sup>3</sup> ]           | x  | x     | x     | x     | x     | x     | x     | 0,268 | 0,258 | 0,287 | 0,263 | 0,287 | 0,248 | 0,268 | 0,287 | 0,229 | 0,244 | 0,258 | 0,272 | 0,287 |
| Covering area of package (smooth edges) [m <sup>2</sup> ] | 30,0   | 15,0  | 10,0  | 7,50  | 6,00  | 5,00  | 4,00  | 3,50  | 3,00  | 3,00  | 2,50  | 2,50  | 2,00  | 2,00  | 2,00  | 1,50  | 1,50  | 1,50  | 1,50  | 1,50  |
| Covering area of package (milled edges) [m <sup>2</sup> ] | x  | x     | x     | x     | x     | x     | x     | 3,34  | 2,87  | 2,87  | 2,39  | 2,39  | 1,91  | 1,91  | 1,91  | 1,43  | 1,43  | 1,43  | 1,43  | 1,43  |

## PARAMETERS

| Board type   |                | Gamma Passive Fasada                           |        |
|--|----------------|--|--------|
| Product code (declared level or class properties of products)          |                | EPS-EN 13163-T1-L2-W2-S <sub>b</sub> 2-P5-BS60 |        |
| Declared product properties conform to EN 13163:2012 standard          | Measuring unit | Requirements or tolerances                     |        |
|  |                | Class or level codes                           | Values |
| Thickness (dimensional tolerance class)                                | [mm]           | T1   | 1      |
| Length (dimensional tolerance class)                                   | [mm]           | L2   | 2      |
| Width (dimensional tolerance class)                                    | [mm]           | W2   | 2      |
| Rectangularity over the length and width (dimensional tolerance class) | [mm/mm]        | S <sub>b</sub> 2                               | 2/1000 |
| Flatness (dimensional tolerance class)                                 | [mm]           | P5   | 5      |
| Flexural strength levels   | [kPa]          | BS60   | 60     |
| Declared thermal conductivity rate                                     | [W/(m·K)]      | [-]  | 0,033  |
| Reaction to fire   | from A to F    | Euroclass                                      | E      |





# GAMMA PASSIVE FASADA

## HEADQUARTERS

YETICO S.A.  
ul. Towarowa 17a  
10-416 Olsztyn

+48 89 538 78 11  
yetico@yetico.com  
www.yetico.com

## CUSTOMER SERVICE

OLSZTYN  
+48 89 538 78 51 / 52

GALEWICE  
+48 62 783 80 89 / 25

GORZÓW WLKP.  
+48 95 720 97 01 / 02

TARNOBRZEG  
+48 539 609 072  
+48 532 916 779